



Device Material Content

5555 NE Moore Ct. Hillsboro OR 97124 custreq@latticesemi.com				Package Code: FTN256 (v.1)			Assembly: ASEM Size (mm): 17 x 17 Lead pitch (mm): 1.0 MSL: 3 Reflow max (°C): 260		
Package: 256 ftBGA Total Device Weight 0.705 Grams		Products: LC4kV/ZC							
November, 2020									
	% of Total Pkg. Wt.	Weight (g)	% of Total Pkg. Wt.	Weight (g)	Substance	CAS #	% of Subst.	Notes / Assumptions:	
Die	1.00%	0.0071			Silicon chip	7440-21-3	100.00%	Die size: 3.35 x 3.35 mm	
Mold Compound	55.31%	0.390	3.32%	0.0234	Epoxy Resin	-	6.00%	Mold Compound: Hitachi CEL9220HF	
			2.77%	0.0195	Phenol Resin	-	5.00%		
			0.11%	0.0008	Carbon Black	1333-86-4	0.20%		
			47.13%	0.3322	Silica	60676-86-0	85.20%		
			1.99%	0.0140	Others	-	3.60%		
D/A Epoxy	0.16%	0.0011	0.13%	0.00088	Silver (Ag)	7440-22-4	80.00%	Die attach epoxy: Henkel (Ablebond) 3230	
			0.03%	0.00022	Organic esters and resins	-	20.00%		
Wire	1.07%	0.0075	1.07%	0.0075	Gold (Au)	7440-57-5	100.00%	0.8 to 1.0 mil diameter; 1 wire per package lead	
Solder Balls	13.78%	0.097	13.30%	0.0937	Tin (Sn)	7440-31-5	96.50%	SAC305	
			0.41%	0.0029	Silver (Ag)	7440-22-4	3.00%		
			0.07%	0.0005	Copper (Cu)	7440-50-8	0.50%		
Substrate	13.11%	0.0924	4.20%	0.0296	BT Resins	-	32.00%	BT Resin CCL-HL832NX-A*	
			8.92%	0.0629	Glass fiber	65997-17-3	68.00%		
Foil	9.56%	0.0674	8.14%	0.0574	Copper	7440-50-8	85.15%		
			1.37%	0.0096	Nickel plating	7440-02-0	14.28%		
			0.05%	0.0004	Gold plating	7440-57-5	0.57%		
Solder Mask	6.01%	0.0424	3.38%	0.0238	Quartz	14808-60-7	56.20%	Solder mask PSR4000 AUS 308	
			0.96%	0.0068	3-methoxy-3-methylbutylacetate	103429-90-9	16.00%		
			1.32%	0.0093	Barium Sulfate	7727-43-7	22.00%		
			0.18%	0.0013	Talc	14807-96-6	3.00%		
			0.03%	0.0002	Naphthalene	91-20-3	0.50%		
			0.14%	0.0010	Trade secret ingredients	-	2.30%		

Lattice regards this materials information to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Lattice subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Lattice has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Lattice products.

www.latticesemi.com

